



Solid Mig/Tig filler metal

Ceweld 316LSi

Type: Stainless steel welding wire developed for welding stabilized austenitic CrNiMo(N) types.

Base metals:	1.4583	X102CrNiMoNb 18 12	316Cb
	1.4435	X2CrNiMo 18 14 3	(TP) 316L
	1.4436	X4CrNiMo 17 13 3	-
	1.4404	X2CrNiMo 17 12 2	(TP) 316L
	1.4401	X4CrNiMo 17 12 2	(TP) 316
	1.4571	X6CrNiMo 17 12 2	316 Ti
	1.4580	X6CrNiMoNb 17 12 3	316Cb
	1.4406	X2CrNiMoN 17 12 3	(TP)316LN

Properties: Excellent corrosion resistance up to 400°C and good weldability with excellent flowing properties due to the increased Si content.

Standards:	AWS SFA 5.9	: ER 316 LSi
	W.Nr.	: 1.4430
	DIN 8556	: SG-X2CrNiMo 19 12
	EN 12072	: G 19 12 3 LSi

Welding positions : according ISO 6947: PA, PB, PC, PD, PE, PF, PG

Shielding gas : according EN 439: M12, - 13

Analyses %

C	Mn	Si	Cr	Ni	Mo
<0.02	1.7	0.8	18.8	12.5	2.8

Mechanical properties

R _{p0,2} (N/mm ²)	R _m (N/mm ²)	A ₅ (%)	Impact strenght ISO-V-J	
			+20 °C	- 196 °C
>380	>560	>35	>70	-

Sizes: Mig: 0,8 mm, 1,0 mm, 1,2 mm, 1,6 mm
Tig: 1,0 – 1,2 – 1,6 – 2,0 – 2,4 - 3,2 mm x 1000 mm

Package: Mig: K-300, D-300, S-300, Drum, B3
Tig: 5 kg cartons

Current Type:
Mig DC +
Tig DC -

Welding products and techniques evolve constantly. All descriptions, illustrations and properties given in this data sheet are subject to change without notice and can only be considered as suitable for general guidance. This document is intended to help the user make the correct choice of product. It is his responsibility to assess its suitability for his intended application